GRABO
1905

Grabolett

Technical datasheet

Entertainment

Technical parameter	Standard	Unit	Result
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	1,7
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m2	2,1
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max.%	±0,2
Curling	EN ISO 23999	max.mm	8
Reaction to fire	EN 13501-1	class	Bfl-s1
Abrasion group	EN 660-1	group	T
Light fastness	EN ISO 105-B02	grade	> 6
Chemical resistance	EN ISO 26987	-	high resistance
Slip resistance	EN 13893	class	DS
Castor chair resistance	ISO 4918 / EN 425		slight change
Surface treatment	CLP SYSTEM		CLP
Antibacterial and fungicid treatment	grabo SAN minimize the growth of microorganisms		graboSAN
Enviromental attributes	SOLVENT FREE		Solvent and heavy metal free product
Warranty		year	3
CE MARKING	**EN 14041**		✓

GRABOPLAST Ltd.
H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
info@grabo1905.com www.grabo1905.com